


T.S.I. LABORATORIES, INC.



TRINITY SOIL INVESTIGATIONS
 901 E. Expressway 83
 La Feria, Texas 78559

Tel: (956) 797-9031
 Fax: (956) 797-2056
 Email: tsi_laferia@sbcglobal.net

Tested For: Innovative Block of So.Tx. Ltd. **Project:** 8" U. Block
 Lt. Wt. Mix Design
 Part #8831XXXX
 Mft. Date: 9-21-07

Lab #: 1107-14-1

REMARKS: On 10-18-07 (6) Concrete Masonry Units were tested. The units sampled were 1 cell 8"x8"x16" nominal. In accordance with ASTM C-140 test procedures. Three units were tested for compressive strength and three units were retained for additional testing if requested. The results are as follows:

<u>Block I.D.</u>	<u>Load (lbs)</u>	<u>Net Area (in²)</u>	<u>Compressive Strength (PSI)</u>	<u>Absorption (%)</u>	<u>Absorption (lbs - ft3)</u>
A	125,940	50.78	2,480	-----	-----
B	110,420	50.78	2,174	-----	-----
C	114,410	50.78	2,253	-----	-----
D	-----	-----	-----	6.82	8.19
E	-----	-----	-----	3.90	4.62
F	-----	-----	-----	12.64	13.06
Average of three (3):			2,302		8.62

ASTM C-90 Requirements

Individual 1700 Minimum
 Average of (3) 1900 Minimum 13.0 maximum

Remarks: The Concrete Masonry Units sampled did or did not meet the compressive requirements strength.



T. S. I. Laboratories, Inc.

[Signature]
 Victor H. Garcia, P.E.